


Presto FF-C18

150 x 4.6 mm


Application

Polyvinyl acetate

ポリ酢酸ビニル



polyvinyl acetate (120 ~ 140 kDa)



Presto FF-C18, 150 x 4.6 mm

A: water

B: acetonitrile

0-100 %B (0-10min), 100 %B (10-15min)

0.4 mL/min (15MPa), 50 deg.C,

ELSD (spray chamber 50 deg.C, drift tube 100 deg.C)

1 uL (5 ug, methanol)