


**Intrada SEC**

250 x 4.6 mm


Application

**SEC: Hydroxypropyl cellulose (HPC)**

ヒドロキシプロピルセルロース(HPC)のSEC分離



hydroxypropylcellulose



Intrada SEC, 250 x 4.6 mm  
 100mM ammonium formate  
 0.3 mL/min (5MPa), 37°C  
 10 μL (5mg/mL, water)